

Physical Property

Grade	Grain size (um)	Co (wt%)	TRS (N/mm ²)	Hardness HV30	K _{1c} (Mpa·m ^{1/2})
XT30S	0.6	12	4800	1540	12.00
AM70	0.6	12	4700	1540	11.75
K44UF	0.4	12	>4000	1690	10



Microstructure

